

GELOCOLLE

PRODUCTS OF FINING

Composition : silicon gel in aqueous dispersion

Aspect : liquid

Color :milky

Dry extract : 29,5 – 30,5 %

pH (25°C) : 8,9 – 9,5

Viscosity (20°C) : < 8 mPa.s

Density : 1,196 – 1,208

Alkalinity (Na₂O) : 0,25 – 0,30 %

Lead : < 5 ppm

Arsenic : < 3 ppm

Mercury : < 1 ppm

Iron : < 90 ppm

Bacteria : < 1000 CFU/g