



# Augmented neutrality

All Qork® stoppers now feature Xpür®, the world's greenest and most efficient anti-TCA technology for micro granulated corks.

Containing a minimum of 80% natural cork granules enveloped by a binding agent with 100% vegetable polyols, Qork® is the world's most sustainable and advanced micro granulated cork stopper.

Featuring Xpür®, the innovative, 21st Century supercritical fluid technology, Qork® allows for a robust and even deeper cleansing of cork's cellular structure, delivering non-detectable TCA performance and eliminating other volatile substances that could trigger sensory deviations, while keeping the natural characteristics of cork intact.




# **SPECIFICATIONS**

Physical – Mechanical Chemical OTR (Oxygen transfer rate) Length (1) Diameter (d) 6 months 0,95 mg of O2  $d \pm 0.4 \,\mathrm{mm}$ I ± 1.0 mm ≤ 0,1 mg/stopper 12 months 1,11 mg of O2 2%-8% ≤0,3 mm ≤2 mg/stopper Specific weight After 12 months  $0,02 \, mg \, of \, O_2^1$ 240 - 320 Kg/m<sup>3</sup> SPMEGC/MS/ECD 1) per year after the 1st year 2, 4, 6 - Trichloroanisol (TCA) Extraction force 15 - 40 daN  $\leq$  0,3 ng/L(\*) CO<sub>2</sub> balance


(\*) Releasable TCA content at or below the 0.3 ng/L detection limit; analysis performed in accordance to an internal method based on ISO 20752.

≈ -393 g/stopper

# PRODUCTION FLOWCHART



# STANDARD DIMENSIONS



# **FOOD STANDARDS**

All Amorim Cork products comply with existing regulations and legislation (European and FDA — Food and Drug Administration) for products in contact with food.

# **RECOMMENDATIONS TO THE USERS**

#### SELECTION AND STORAGE OF CORK STOPPERS

Amorim can calculate the required cork diameter by studying the internal profile of the bottleneck, the characteristics of the wine and the corking conditions.

Order your cork stoppers for immediate use. These cork stoppers should be used within six months of the date of manufacture if the storage conditions are respected.

Store the cork stoppers in their original packages, in a well-ventilated room with controlled temperature between 15°C and 25°C and 50% to 70% humidity.

Do not leave boxes and/or bags open with surplus cork stoppers.

## CORKING CONDITIONS

Ensure any dust its removed before corking.

Ensure the cork is compressed smoothly, to a diameter no less than 15,5 mm.

Ensure insertion of the  $\operatorname{cork}$  is a quick as possible.

For standard bottlenecks, the cork should be inserted to 1 mm below the top of the neck.

 $Minimise\ moisture\ on\ the\ inside\ of\ the\ bottleneck.$ 

Headspace should be at least 15 mm at 20  $^{\circ}$ C.

Don't leave the cork stoppers in the feeder as to avoid dust.

Always use stoppers with a surface treatment suitable for the type of beverage, bottling process and selected bottle.

A vacuum must be created in order to prevent internal pressures.

# Please always check the most updated version of the technical sheet of the product you are using as the manufacturer reserves its right to implement product changes without prior notice.

#### **EQUIPMENT MAINTENANCE**

 $\label{thm:maintain} \mbox{ Maintain the corker jaws free of nicks and signs of wear.}$ 

Ensure proper alignment of plunger and location ring.

 $Ensure\ corking\ machine\ operates\ smoothly, especially\ during\ compression.$ 

Clean all cork-handling surfaces regularly with chlorine-free products.

Ensure the equipment is suited to the cork and bottle used.

### STORAGE AND TRANSPORT OF WINE

 $After bottling, the bottles should be kept in an upright position for at least 10 \,minutes.$ 

Ideal bottle storage conditions are 12°-18°C at 50-70% humidity.

Keep the wine cellar free of insects.

Bottles should be transported in an upright position.

The product must not be stored in a location exposed to sunlight, heated environment and in direct contact with the ground.













Amorim Distribuição

par Equipar
rim Champcork Amorim Cha
rimTopSeries AmorimTopS
ocork Lamas

Equipar Amorim Champcork Amorim Top Series

Amorim Distribuição